

## Roof Sealant DD

Properties	Value	Unit	Method / Remarks
	System		
Chemical Base	bituminous elastomer		
Curing System	physical drying		
Tack Free Time	> 15	h	+ 23 °C / 55 % RLH
Density	1,3	g/ml	
Consistency	pasty		
Application Temperature	+ 5 to + 40	°C	optimal + 5 °C to + 20 °C
Temperature Resistance	- 20 bis + 80	°C	fully cured
Solids	85	%	
Shelf Life	12	months	+ 5 to + 25 °C

### Product Details

fischer Roof Sealant DD is an one part bituminous elastomer sealant, which dries physically by evaporation of a solvent. It shows excellent adhesion to many substrates in particular to bituminous surfaces and can be applied to wet surfaces. It is suitable as cold setting adhesive for all kinds of roofing cardboard.

### Direction of Use

Surfaces must be clean, free of dust and grease, but may be wet. A pre-treatment is not necessary, however adhesion tests are recommended. Fischer Roof Sealant DD adheres to all common construction surfaces. fischer DD can be used for bonding bituminous shingles and for carrying out emergency repairs on roofs, gutters, chimneys, etc. Not suited for use on underwater joints, PE, PP and Teflon.

For further safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

The information in this adhesives brochure and our application-technology consulting, verbally and in writing, is given to the best of our knowledge, but is non-binding and is not a guarantee in the sense of § 443 BGB. We recommend that, before using our products, you check the suitability for the intended application. As the individual product can be used for a wide range of applications and the conditions on site that cannot be estimated, we also recommend testing the bonding before using the product.

DD

version: 3/2011-05-11